

NovaLiner® 30

12.2 OZ GEOMEMBRANE



PRODUCT DESCRIPTION

A heavyweight fabric incorporating a special weave pattern to enhance tpuncture, flatness, and tear properties. The coating recipe is designed to improve toughness and abrasion resistance. This product is intended for exposed applications up to 10 years.

RECOMMENDED APPLICATIONS

Interim Landfill Covers. Containment Liners

PRODUCT DIMENSIONS

4 inch I.D. or 5 inch I.D. available (10 cm or 13 cm) Cores

Width Up to 150 in (381 cm) (-0, +0.5) as ordered

Length Minimum 250 yds/roll (229 m); up to 1000 yds/roll (914 m)

PRODUCT SPECIFICATIONS

Weave Woven black HDPE scrim

Coating LDPE, 4 mil average each side (95 g/m²/side)

White, black or other colored coatings available Color Weight

 $12.2 \text{ oz/yd}^2 (414 \text{ g/m}^2) \pm 5 \%$



These values are typical data and are not intended as limiting specifications.



PERFORMANCE PROPERTIES

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	Nominal 30 mil (0.75 mm) ± 10%
Grab Tensile (N) ASTM D7004	MD 282 lb (1252) TD 320 lb (1421)
Strip Tensile (N/5cm) ASTM D7003	MD 188 lb/in (1669) TD 225 lb/in (1998)
Tongue Tear-large scale (N) ASTM D5884	MD 70 lb (311) TD 85 lb (377)
Mullen Burst ASTM D751	585 psi (4031 kPa)
MVTR ASTM E96 Proc. BW	0.21 g/m ² ·24hr (0.03 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	1.46 x 10 ⁻¹⁴ cm/s
Hydrostatic Resistance ASTM D751	423 psi (2914 kPa)
Puncture Resistance ASTM D4833	165 lb (733 N)
CBR Static Puncture ASTM D6241	1025 lb (4551 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -2.2% TD -1.6%
Low Temperature Flex ASTM D2136	MD & TD Pass @ -65°C (-85°F)
HP-OIT ASTM D5885 (Measured on coating formula)	1071 minutes
Accelerated UV Weathering ⁱ ASTM D7238	>90% tensile strength retention after 10,000 light hours

MD = Machine Direction. TD = Transverse Direction. $^{\rm i}$ Q.U.V [A-340 Lamps]; 20 hrs UV @ 75°C; 4 hrs condensation @ 60°

Please contact your IPG representative for warranty details.











These values are typical data and are not intended as limiting specifications.

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

