

Stretch Film

HWII (Hand Wrap II - HR)

INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

Test	Values (listed by film thickness)							
	Reference Methods	65 gauge 16.5 micron 0.65 mil	70 gauge 17.8 micron 0.70 mil	80 gauge 20.3 micron 0.80 mil	90 gauge 22.9 micron 0.90 mil	100 gauge 25.4 micron 1.00 mil	110 gauge 27.9 micron 1.10 mil	120 gauge 30.5 micron 1.20 mil
Ultimate Tensile MD (psi)	ASTM D882	6150	6200	6200	6300	6380	6450	6500
Ultimate Tensile TD (psi)	ASTM D882	4650	4000	4800	4900	4910	5000	5200
Elongation MD (%)	ASTM D882	480	500	500	600	715	625	625
Elongation TD (%)	ASTM D882	640	650	670	735	810	750	775
Tear Resistance MD (grams and g/mil)	ASTM D1922	40 grams	42 grams	90 grams	92 grams	92 grams	97 grams	105 grams
		61.5 g/mil	60 g/mil	113 g/mil	102 g/mil	92 g/mil	88.2 g/mil	87.5 g/mil
Tear Resistance TD (grams and g/mil)	ASTM D1922	474 grams	530 grams	350 grams	320 grams	337 grams	350 grams	375 grams
		729 g/mil	757 g/mil	438 g/mil	356 g/mil	337 g/mil	318 g/mil	313g/mil
Dart Drop (grams and g/mil)	ASTM D1709	50 grams	58 grams	61 grams	65 grams	73 grams	75 grams	82 grams
		76.9 g/mil	82.9 g/mil	76.3 g/mil	72.2 g/mil	73 g/mil	68.2 g/mil	68.3 g/mil
Pre-stretch (% at break)	IPG/Highlight	220	265	275	285	300	325	350
Cling (in to out, grams at 200% pre-stretch)	IPG method	250 grams	250 grams	250 grams	225 grams	225 grams	225 grams	225 grams

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA
 Customer Service: 800.IPG.8273 | 800.474.8273
www.itape.com | info@itape.com

EFFECTIVE: 4/13/20

